

AC698

PREMIUM BOPP FILM HVAC TAPE

DESCRIPTION

Acrylic based pressure-sensitive adhesive combined with the conformability/flexibility of biaxially-oriented polypropylene (BOPP) film provides superior sealing, protective benefits, and ease of handling. Printed for easy identification/inspection and resistant to mold growth and high humidity. Designed and engineered for use on Class 1 flexible duct for permanent seaming and sealing to enhance appearance and provide barrier protection. All temperature rates, flame retardant, high shear, aggressive, and UV resistant. Superior bonding at sub-zero or at elevated temperatures. UV/temperature resistant acrylic adhesive combined with inorganic polypropylene film provides the longest lasting closure method.

PRODUCT APPLICATION

HVAC (Heating, Ventilation, and Air Conditioning) applications. Intended for use on UL listed flexible duct (or other) meeting UL-181 standards.

GOVERNMENT COMPLIANCE

UL Listed: 181B-FX



intertape polymer group®

100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA

Customer Service: 800.IPG.8273 | 800.474.8273

Tape Technical Service: 877.447.4832

www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 02/15

INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

Backing	40 micron BOPP
Adhesive	Emulsion Acrylic
Adhesion to Steel (oz/in of width) ASTM D3330	33.5 (9.2 N/25mm)
Tensile Strength (lbs/in of width) ASTM D3759	29 (127 N/25mm)
Elongation (% at break) ASTM D3759	117.5
Total Thickness (mils) PSTC-133	3 (0.076mm)
Shear (100gm wt. @ 150°F)-minutes ASTM D3654	>22
Surface Burn	
Flame Spread UL 723/ASTM E-84	3
Smoke Generated UL 723/ASTM E-84	0
Mold Growth & Humidity Spread UL 181 B-Part 1	0
Temperature Test (212°F/60 days) deterioration, brittleness, cracking, flaking, blistering. UL 181 B-Part 1	0
Operational Temperature -65°F to +212°F (-54°C to +100°C)	

Colors

Black w/ white print,
Clear w/ red print,
Metalized (silver) with
burgundy print

